

Product Information

VESTAMID® *Terra* DS18 natural color

Medium viscosity polyamide 1010

VESTAMID *Terra* DS18 natural color is a medium viscosity PA 1010 basic polymer. VESTAMID *Terra* DS18 is semi-crystalline, which is the reason for its high mechanical resistance and chemical stability. It absorbs only little water. As a result its mechanical properties vary little when exposed to changing environmental humidity, and the material features a high dimensional stability.

VESTAMID *Terra* DS18 can be used to manufacture films with good transparency.

The high melting point of VESTAMID *Terra* DS18 compounds results in a high heat deflection temperature that can be advantageous for some applications.

VESTAMID *Terra* DS18 occupies a position between the high-performance long-chain polyamides such as PA 12 and PA 1212 and the standard polyamides PA 6 and PA 66, which have a shorter chain length.

Because of its chemical and physical properties, and the plant origin of its monomers, VESTAMID *Terra* DS18 is an interesting addition to conventional longer-chain polyamides, and it also meets the growing demand for materials made from renewable raw materials.

VESTAMID *Terra* DS18 natural color is supplied as cylindrical granules, ready for processing, in moisture-proof bags.

VESTAMID® Terra is a group of new polyamides, the monomers for which are based entirely or partly on renewable raw materials.

VESTAMID® Terra DS is the polycondensation product of 1,10-decamethylene diamine (D) and 1,10-decanedioic acid (sebacic acid—S). Because both monomers are extracted from castor oil, VESTAMID® Terra DS is based on natural, renewable resources up to 100%.

For further information, please contact our experts in the department Market Development of the High Performance Polymers Business Line.

Property	Test method		Unit	VESTAMID <i>Terra</i> DS18	
	international	national			
Density	23°C	ISO 1183	DIN EN ISO 1183	g/cm ³	1.05
Tensile test		ISO 527-1	DIN EN ISO 527-1		
Stress at yield		ISO 527-2	DIN EN ISO 527-2	MPa	54
Strain at yield				%	5
Strain at break				%	> 50
Tensile modulus		ISO 527-1	DIN EN ISO 527-1	MPa	1700
		ISO 527-2	DIN EN ISO 527-2		
CHARPY impact strength		ISO 179/1eU	DIN EN ISO 179/1eU		
	23°C			kJ/m ²	N ¹⁾
	-30°C			kJ/m ²	N ¹⁾
CHARPY notched impact strength		ISO 179/1eA	DIN EN ISO 179/1eA		
	23°C			kJ/m ²	7 C ¹⁾
	-30°C			kJ/m ²	7 C ¹⁾
Vicat softening temperature		ISO 306	DIN EN ISO 306		
Method A	10 N			°C	196
Method B	50 N			°C	171
Water absorption		ISO 62	DIN EN ISO 62		
	saturation			%	1.8
Viscosity number		ISO 307	DIN EN ISO 307	cm ³ /g	180
Melting range		ISO 11357			
DSC	2 nd heating			°C	200
Percentage of Renewable Carbon (calculation)		ASTM 6866		%	100
Global Warming Potential (GWP)*		Evonik, PE International		kg CO ₂ equivalents/ kg material	2.8

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.

*preliminary data

¹⁾ C = Complete break, incl. hinge break H
N = No break

® = registered trademark

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. Evonik shall not be responsible for consequential, indirect or incidental damages (including loss of profits) of any kind. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.